

### General Description

ADFORS GlasGrid GG non-adhesive is the product for special application on surfaces covered by mastic asphalt. The product is manufactured at a Saint-Gobain ADFORS facility that has achieved ISO 9001:2015 certification and meets the requirements of EN 15381. ADFORS GlasGrid is a high strength, open fiberglass grid custom knitted in a stable construction and coated with a patented elastomeric polymer. Every component of the matrix shall be stabilized against ultraviolet degradation and inert to chemicals normally found in a natural soil environment. ADFORS GlasGrid conforms to the property values listed below, which have been derived from quality conformance testing performed by a laboratory:

### Technical Characteristics

Property	Unit	GG 50 NA	Test Method
Tensile Strength (MD x XD) Ultimate	kN/m	(55 x 55) - 5	EN ISO 10319
Tensile Elongation Ultimate	%	2,5 ± 0,5	EN ISO 10319
Tensile Resistance @ 2% Strain (MD x XD)	kN/m	(46 x 46) ± 10	EN ISO 10319
Secant Stiffness EA @ 1% Strain (MD x XD)	N/mm	(2.200 x 2.200) ± 200	EN ISO 10319
Young's Modulus E	MPa	73.000	
Mass per Unit Area	g/m <sup>2</sup>	205	EN ISO 9864
Melting Point Coating	°C	>232	ASTM D 276
Roll Length	m	150	
Roll Width	m	1,5	
Roll Area	m <sup>2</sup>	225	
Grid Size (Center to Center of Strand)	mm	25 x 25	
Material	Fiberglass reinforcement with modified polymer coating		

### Properties

- High grid stiffness provides a wrinkle-free installation and a direct load transmission
- Low elongation
- Thermal and chemical stability
- Excellent milling performance



The values and tolerances given are obtained in our laboratories and in accredited testing institutions. The information given in this data sheet is to the best of our knowledge true and correct. However new research and practical experience can make revisions necessary. We reserve the right to make changes at any time. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, expressed or implied, is made or intended.

## Installation

- Unroll and lay the geogrid on dry and clean flat layer/leveling course.
- Respect the overlap of end roll joints 10 - 15 cm and longitudinal joints at minimum 5 cm.
- Apply mastic asphalt layer.

## Benefits

- Elimination of flowing of mastic asphalt during the hardening
- Protection against microcracking in mastic asphalt
- Quick and efficient installation
- Easy cutting
- Thermal and chemical stability
- Excellent milling performance
- Measured unlimited recyclability & enhanced properties in Reclaimed Asphalt Pavement (RAP)

## Palletization

Product	Roll width	Roll area	Roll weight	Core inner diameter	No of rolls on pallet	Total area
GG 50 NA	1,5 m	225 m <sup>2</sup>	51 kg	76 mm	12	2 700 m <sup>2</sup>



**SAINT-GOBAIN ADFORS CZ s.r.o.**  
 Sokolovská 106  
 570 01 Litomyšl  
 Czech Republic  
 Tel: +420 461 651 111  
[glasgrid.cz@saint-gobain.com](mailto:glasgrid.cz@saint-gobain.com)  
[eu.adfors.com](http://eu.adfors.com)

In as much as Saint-Gobain ADFORS has no control over installation design, installation workmanship, accessory materials, or conditions of application, Saint-Gobain ADFORS does not warrant the performance or results of any installation or use of ADFORS GlasGrid. This warranty disclaimer includes all implied warranties, statutory or otherwise, including the warranty of merchantability and of fitness for a particular purpose. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product for the particular purpose desired in any given situation.

**CE** Plant Litomyšl (CZ):  
 1021-CPR-040/15-1  
 15



ADFORS GlasGrid® is manufactured at an ISO 9001:2015 registered facility of Saint-Gobain ADFORS. ADFORS GlasGrid® is a registered trademark of Saint-Gobain ADFORS. U.S. Patent 8,038,364; 8,349,431 and 8,882,385. Additional patents pending.  
 © 2021 Saint-Gobain ADFORS

**TROUBLE WITH YOUR ROAD?**

Try the GlasGrid app to fix it!

